



Compashield® splice quality requirements:

No reduction of the shielding properties in the splicing area. Splicing rubber thin and conductive.
 No flash, porosity or excess rubber at the joint after splicing.
 Max increase of compression force in the splicing area 5%. No excess splicing rubber inside hollow profiles.
 Joining point should stand for 10% stretch without mechanical damage



Cross-section area

2,41mm²**Electrial resistance measure:**

Methode: Nolato R3 Max:150 mOhm



REVISIONS			Art.nr	Material	Lenght	Weight/m	Splice
REV.	DATE	DESCRIPTION	1179600	8605	Roll	2,41	No

		Document name					
		Compashield Solid O-shape					
		Sheet scale	Sheet size	Document no.	Rev no.	Nalato art. no.	Customer no.
		10:1	A4	P1796:11:001	B	1179600	
General tolerances				Drawn by	Checked by	Date	
ISO 3302-1 M3				K.Muhonen	P.Akerberg	2013-06-13	
				Reference cad data	Part version no.		