

Data Sheet Compatherm Potting 9110

Compatherm filler 9110 is a thermally conductive two-part addition cured potting material from Nolato. Compatherm filler 9110 is delivered as A and B component.

Compatherm filler key properties 9110

- 1 W/(mK) thermal conductivity
- Operating temperature -40 to +150° C
- Very low viscosity
- Self-levelling
- Two-part material gives high mechanical stability after curing

1. Applications

The product is used to transfer heat from heat sources and protect components from environment impact and vibrations.

2. Typical Product Data

2.1. Cured Material Properties

	Test procedure	Unit	9110
Base material			Silicone
Colour	Visual		Pink
Hardness	ASTM D2240	ShoreA	20
Density	ASTM D792	g/cm ³	1.77
Thermal conductivity	ISO 22007-2 (Hot Disk)	W/(mK)	1
	ASTM D5470	W/(mK)	1
Volume resistivity	ASTM D 257	Ωcm	1.42*10 ¹³
Breakdown voltage	ASTM D149	VAC/mm	7000
Dielectric constant at 1MHz	ASTM D150		4.75
Outgassing, TML ¹⁾	ASTM E595 (modified)	%	0.6
Flammability ²⁾	UL94		V0

1) Outgassing 24h at 150 °C under ambient pressure. 2) Tested at external lab.

2.2. Uncured Material Properties

	Test procedure	Unit	9110
Mix ratio			1:1
Colour component A	Visual		White
Colour component B	Visual		Pink
Component A	10s ⁻¹	Pas	15
Component B	10s ⁻¹	Pas	15
Viscosity (mixed)	10s ⁻¹	Pas	24
BLT @40psi		mm	0.11

2.3. Design Notes

Curing	Test procedure	Unit	9110
Pot life at 25 ° C	Nolato	h	1
Curing time at 25° C	Nolato	h	24
Curing time at 100° C	Nolato	min	20

3. Ordering

When ordering Compatherm material please refer to the thermal guide (<https://thermalguide.nolato.com/>) or consult the Nolato marketing department.

4. Storage

Compatherm filler 9110 can be stored 8 months after production date at 0 to 30°C. Cartridges are recommended to be stored nozzle down. Only components A and B with the same lot number may be processed together.

Some degree of sedimentation can occur over time. If sedimentation is suspected additional stirring/mixing of the A and B components in pales is recommended to ensure homogeneous properties of the cured filler.

5. RoHS Information

Compatherm filler 9110 fulfils the requirements set by the EU Directive 2011/65 (RoHS).

6. Safety Instructions

Compatherm filler 9110 is not considered as hazardous according to EU Directive 1272/2008 (CLP) and is not subject to the directive of classification, packaging and labelling of dangerous goods. A material safety data sheet can be sent on request.

7. Warranty

The recommendations and data given are based on our experience to date, however, no liability can be assumed in connection with their usage and processing. The typical property data as shown above should not be used as a specification.